

POLYSULFONE SHEET MEMBRANE PRODUCTS

High Performance FDA-Approvable PS Sheet Membrane

SPECIFICATIONS

FDA-approvable Polysulfone Membrane for Food, Pharmaceutical, and Industrial Uses

PHYSICAL PROPERTIES

Thickness (including backing fabric):	0.0065 in (0.165 mm)
Active Membrane Width:	40.0 in (1.02 m)
Optional Roll Slit Widths:	10 or 20 in (254 or 508 mm)
Roll Length (Increments):	410 ft (125 m)

PERFORMANCE PROPERTIES*

MODEL NUMBER	WATER FLUX (Lmh / bar)	MW of MARKER (Dalton)	MARKER REJECTION (%)
PS20	900	20K PEG**	95
PS30	1,200	20K PEG**	96
PS35	1,600	20K PEG**	98

OPERATING PARAMETERS

Process pH Limitations:	2.0-10.0
CIP pH Limitations:	1.5-11.5
Maximum Process Temperature:	122°F / (50°C)

CLEANING LIMITS***

CLEANERS	CIP		
	Concentration (ppm)	pH	Maximum Temperature
Chlorine	500	11.5	122 °F (50 °C)
Peracetic acid & H ₂ O ₂	2000 (500 as H ₂ O ₂)	3-7	77°F (25°C)

* Tests conducted at 30 psi and 77°F (25°C) using non-fouling RO permeate for water flux, with 2000 ppm concentration of marker added for rejection characterization.

** PEG: Poly(ethylene glycol)

*** Consult factory for detained cleaning instructions.

Note: Sepro's membrane products are not designed to be sterilized or disinfected.

PSsheet05 3/10