

POLYVINYLIDINE FLUORIDE SHEET MEMBRANE PRODUCTS

High Performance FDA-Approvable PVDF-MFB and PVDF-MF Sheet Membrane

SPECIFICATIONS

FDA-approvable Polyvinylidene fluoride Membrane for Food, Pharmaceutical, and Industrial Uses

PHYSICAL PROPERTIES

Thickness (including backing fabric):	0.00725 in (0.184 mm)
Active Membrane Width:	40.0 in (1.02 m)
Optional Roll Slit Widths:	10 or 20 in (254 or 508 mm)
Roll Length (Increments):	410 ft (125 m)

PERFORMANCE PROPERTIES*

MODEL NUMBER	WATER FLUX (Lmh / bar)	MW of MARKER (Dalton)	MARKER REJECTION (%)
PVDFMFB	1,800		Pore Size: 0.2-0.4 μm
PVDFMF	10,000		Pore Size: 0.5-0.7 μm

OPERATING PARAMETERS

Process pH Limitations:	2.0-10.0
CIP pH Limitations:	1.5-11.5
Maximum Process Temperature:	122°F (50°C)

CLEANING LIMITS***

CLEANERS	CIP		
	Concentration (ppm)	pH	Maximum Temperature
Chlorine	500	11.5	122°F (50°C)
Peracetic acid & H ₂ O ₂	2000 (500 as H ₂ O ₂)	3-7	77°F (25°C)

* Tests conducted at 6 psi and 77°F (25°C) using non-fouling RO permeate for water flux

** PVA — Poly(vinyl alcohol)

*** Consult factory for detailed cleaning instructions

Note: Sepro's membrane products are not designed to be sterilized.

PVDFSHEET rev1 4/10